

# Open Circuit Voltage Vs State of Charge

Using a Digital Voltmeter				
% Charge	Flooded Type		Absorb / SLA Type	Gel Type
-	Calcium/Calcium	Lead Antimony	-	-
100	12.80	12.65	12.90 - 12.80	12.95 - 12.85
75	12.65	12.45	12.60	12.65
50	12.44	12.24	12.30	12.35
25	12.19	12.06	12.00	12.00
0	11.97 or less	11.89 or less	11.80	11.80

**Note:** Divide values in half for 6-volt batteries. The true open circuit voltage of a battery can only be determined after the battery has been removed from the load (charge or discharge) for 24 hrs.

Copyright HCB Technologies 2017. All rights reserved. No part of this article may be changed or reproduced without prior permission from HCB Technologies Head Office. [info@hcb.co.nz](mailto:info@hcb.co.nz)